# UL Product iQ®

# Model OROGLAS, ALTUGLAS

File Number: E248976



#### **COMPANY**

## Trinseo Europe GmbH

Zugerstrasse 231 Horgen, Zurich 8810 Switzerland

### **MODEL INFO**

### OROGLAS, ALTUGLAS

Polymethyl Methacrylate (PMMA), furnished as sheets

MMABILITY PROPERTIES	VALUE	TEST METHOD
lammability		ANSI/UL 94
1.5 mm, Color: ALL	НВ	
3.0 mm, Color: ALL	НВ	
O/IEC FLAMMABILITY PROPERTIES	VALUE	TEST METHOD
lammability		IEC 60695-11-10
1.5 mm, Color: ALL	HB75	
3.0 mm, Color: ALL	HB40	
HERMAL PROPERTIES	VALUE	TEST METHOD

Relative Thermal Index - Electrical Strength		UL 746B
1.5 mm	50 °C	
3.0 mm	50 °C	
Relative Thermal Index - Mechanical Impact		UL 746B
1.5 mm	50 °C	
3.0 mm	50 °C	
celative Thermal Index - Mechanical Strength		UL 746B
1.5 mm	50 °C	
3.0 mm	50 °C	

Report Date: 2004-08-03 Revision Date: 2023-03-30

The appearance of a company's name or product in this database does not in itself assure that products so identified have been manufactured under UL Solutions' Follow - Up Service. Only those products bearing the UL Mark should be considered to be Certified and covered under UL Solutions' Follow - Up Service. Always look for the Mark on the product.

UL Solutions permits the reproduction of the material contained in Product iQ subject to the following conditions: 1. The Guide Information, Assemblies, Constructions, Designs, Systems, and/or Certifications (files) must be presented in their entirety and in a non-misleading manner, without any manipulation of the data (or drawings). 2. The statement "Reprinted from Product iQ with permission from UL Solutions" must appear adjacent to the extracted material. In addition, the reprinted material must include a copyright notice in the following format: