

Ref: MKO/LT08-044a

Date: April 18, 2008

**Subject: LEXAN\* SG305OB/EXELL\* D OB and Glow Wire testing**

Dear Customer,

Based on in-house testing we can confirm that following grades will have a Glow Wire Flammability Index according IEC 60695-2-12.

Grade	Thickness	GWFI
LEXAN* SG305OB / LEXAN* EXELL* D OB	2-4 mm	850 °C
LEXAN* SG305OB / LEXAN* EXELL* D OB	5-6 mm	960 °C

Both mentioned grades are formulated without the use of flame retardant additives

I hope to have informed you accordingly.

Yours faithfully,



Ir. M.F.M. Koppers  
Global Agency Relations

\* trademark of SABIC Innovative Plastics IP BV.

SABIC Innovative Plastics B.V.  
PO Box 117, 4600 AC  
Plasticslaan 1, 4612 PX  
Bergen op Zoom  
Netherlands  
T: +31 164 291302  
F: +31 164 292194  
E: thijs.koppers@sabic-ip.com  
www.sabic-ip.com

**ANY SALE OF PRODUCTS OR DELIVERY OF CUSTOMER SUPPORT AND ADVICE BY SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), IS MADE EXCLUSIVELY UNDER SELLER'S STANDARD CONDITIONS OF SALE** which can be located at <http://www.sabic-ip.com>. **SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OF ITS PRODUCTS IN ANY CUSTOMER'S APPLICATION.** Each customer should determine the suitability of SELLERS materials for the customer's particular use through appropriate testing and analysis.