

PET & PETG CHEMICAL RESISTANCE

The data below concerning the chemical resistance of PET and PETG has been obtained from publically available data sources. The data should be treated with caution and should only be regarded as an indication of the chemical resistance since the resistance performance can be affected by many factors, such as temperature, concentration, and whether the samples are under stress. It is also difficult to predict the resistance against compounds containing several different chemicals.

Resistance: 1 = stable, 2 = conditionally stable, 3 = unstable

| Contents | Conc. | PETG | |
|-----------------------------------|-------------|---------|---------|
| | | @ 20 °C | @ 50 °C |
| Acetaldehyde | 40% | 3 | 3 |
| Acetic acid | 10 % | 1 | 1 |
| Acetic acid | 5 % | 1 | 1 |
| Acetic acid (glacial acetic acid) | 90% | 3 | 3 |
| Acetic acid ester | 100 % | 3 | 3 |
| Acetone | | 3 | 3 |
| Acetonitrile | | - | 3 |
| Acid, battery | 38 % | 3 | 3 |
| Allyl alcohol | 96 % | 1 | - |
| Alum | | 1 | 1 |
| Aluminium chloride | 10 % | 1 | 1 |
| Aluminium chloride | aqueous | 1 | 1 |
| Aluminium nitrate | aqueous | 1 | 1 |
| Aluminium sulfate | 10 % | 1 | 1 |
| Ammonia | 25 % | 1 | 3 |
| Ammonia liquor | any | 1 | 3 |
| Ammonium chloride | aqueous | 1 | 1 |
| Ammonium fluoride | saturated | 1 | 1 |
| Ammonium fluoride | aqueous | 1 | 1 |
| Ammonium nitrate | 10 % | 1 | 1 |
| Ammonium nitrate | saturated | 1 | 1 |
| Ammonium nitrate | aqueous | 1 | 1 |
| Ammonium sulfate | 10 % | 1 | 1 |
| Ammonium sulfate | saturated | 1 | 1 |
| Ammonium sulfate | aqueous | 1 | 1 |
| Amyl acetate (Pentylacetate) | | 1 | 2 |
| Amyl alcohol | | 1 | - |
| Antifreeze (Ethyleneglycol) | | 1 | - |
| Aqua regia | | 3 | 3 |
| Beer | | 1 | - |
| Benzene | | 3 | 3 |
| Benzoic acid | saturated | 1 | - |
| Benzoic acid | aqueous | 1 | - |
| Borax | any | 1 | 1 |
| Boric acid | 10 % | 1 | - |
| Boric acid | aqueous | 1 | - |
| Brake fluid DOT 3 | | 1 | 1 |
| Brandy | | 1 | - |
| Bromic vapours | | 3 | 3 |
| Bromine | | 3 | 3 |
| Butane | techn. pure | 1 | - |
| Butanol | techn. pure | 1 | - |
| Butinediol | 10 % | 1 | - |
| Butyl acetate | | 2 | - |
| Calcium chloride | aqueous | 1 | - |

| | | | |
|------------------------------|-------------|---|---|
| Calcium hypochlorite | aqueous | 2 | - |
| Calcium hypochlorite | saturated | 2 | - |
| Calcium nitrate | 50 % | 1 | 1 |
| Calcium nitrate | aqueous | 1 | 1 |
| Carbon dioxide, dry | techn. pure | 1 | 1 |
| Carbon dioxide, umid | techn. pure | 1 | 1 |
| Carbon tetrachloride | | 1 | 3 |
| Carbonic acid | saturated | 1 | 1 |
| Caustic potash | 30 % | 3 | 3 |
| Caustic potash | 50 % | 3 | 3 |
| Caustic potash | aqueous | 3 | 3 |
| Caustic potash | 10 % | 3 | 3 |
| Caustic potash | 50 % | 3 | 3 |
| Caustic soda | | 3 | 3 |
| Chlorinated water | | 3 | 3 |
| Chlorine | 10 % wet | 3 | 3 |
| Chlorine | 97 % | 3 | 3 |
| Chlorine gas | | 3 | 3 |
| Chloroacetic acid | | 3 | 3 |
| Chloroacetic acid (mono) | 50 % | 3 | 3 |
| Chloroacetic acid (mono) | techn. pure | 3 | 3 |
| Chlorobenzene | | 1 | 3 |
| Chlorsulphonic acid | techn. pure | 3 | 3 |
| Chromic acid | 10 % | 2 | - |
| Chromic acid | 20 % | 3 | 3 |
| Chromic acid | 50 % | 3 | 3 |
| Chromic acid | aqueous | 3 | 3 |
| Chromic alum | saturated | 1 | 1 |
| Chromic sulphuric acid | pur | 3 | 3 |
| Citric acid | 10 % | 1 | 2 |
| Citric acid | 10 % | 1 | 2 |
| Common salt | | 1 | 1 |
| Common salt | aqueous | 1 | 1 |
| Copper sulphate | aqueous | 1 | 1 |
| Crude oil | 100 % | 1 | - |
| Cyclanone | | 1 | 1 |
| Cyclohexane | | 1 | - |
| Cyclohexanone | techn. pure | 3 | 3 |
| Dekalin (Decahydronaphtalin) | 100 % | 2 | - |
| Detergent solution | | 1 | 1 |
| Dextrine | | 1 | 1 |
| Dextrine | aqueous | 1 | 1 |
| Dibutyl phthalate (DBP) | | 1 | - |
| Dichloroethylene | techn. pure | 3 | 3 |
| Diesel oil | 100 % | 1 | 1 |
| Dimethyl formamide | | 1 | - |
| Dioxane | | 1 | - |
| Emissions, carbon dioxide | low | 1 | 1 |
| Engine oil | | 1 | 1 |
| Ethanol | 50 % | 1 | 1 |
| Ethanol | 96 % | 1 | 1 |
| Ethyl acetate | | 2 | 3 |
| Ethyl alcohol | 40 % | 1 | 1 |
| Ethyl alcohol | 96 % | 1 | 1 |
| Ethyl chloride | | 3 | 3 |
| Ethylene glycol | | 1 | - |
| Fat, vegetable | | 1 | - |

| | | | |
|------------------------------|-------------|---|---|
| Fatty acid | techn. pure | 1 | - |
| Fertilizer salts | saturated | 1 | - |
| Fluorhydric acid | 100 % | 3 | 3 |
| Fluorhydric acid | 4 % | 3 | 3 |
| Fluorhydric acid | 50 % | 3 | 3 |
| Fluorine | | 3 | 3 |
| Fluorine | dry | 3 | 3 |
| Formaldehyde | 10 % | 1 | - |
| Formaldehyde | 40 % | 1 | - |
| Formic acid | 3 % | 1 | - |
| Fruit juices | | 1 | - |
| Fruit wine | | 1 | 1 |
| Gelatine | any | 1 | 1 |
| Gelatine | aqueous | 1 | 1 |
| Glacial acetic acid | | 3 | 3 |
| Glucose | any | 1 | 1 |
| Glue (animal glue, gelatine) | any | 1 | 1 |
| Glycerin | any | 1 | - |
| Glykol | | 1 | - |
| Grape sugar | any | 1 | 1 |
| Grape sugar | aqueous | 1 | 1 |
| Hexane | | 1 | - |
| Hexane, -n | | 1 | - |
| Hydrobromic acid | 40% | 3 | 3 |
| Hydrobromic acid | 50 % | 3 | 3 |
| Hydrobromic acid | diluted | 2 | - |
| Hydrochloric acid | 1-5 % | 1 | 1 |
| Hydrochloric acid | 20 % | 2 | - |
| Hydrochloric acid | 35 % | 3 | 3 |
| Hydrochloric acid | conc. | 3 | 3 |
| Hydrofluosilicic acid | 32 % | 3 | 3 |
| Hydrogen fluoride | anhydrous | 3 | 3 |
| Hydrogene chloride gas | | 3 | 3 |
| Hydrosulphide | saturated | 1 | - |
| Isooctane | techn. pure | 1 | - |
| Kerosene | | 1 | - |
| Kerosene | | 1 | 1 |
| Lactic acid | 3 % | 1 | - |
| Lactic acid | aqueous | 1 | - |
| Lead acetate | aqueous | 1 | 1 |
| Lead-(II)-acetate | | 1 | 1 |
| Linseed oil | techn. pure | 1 | - |
| Liqueurs | | 1 | - |
| Lubricating oil | | 1 | 1 |
| Magnesium sulphate | saturated | 1 | 1 |
| Magnesium sulphate | aqueous | 1 | - |
| Magnesium chloride | aqueous | 1 | - |
| Mercury | pur | 1 | 1 |
| Mercury chloride | aqueous | 1 | 1 |
| Methanol | | 1 | - |
| Methyl acetate | techn. pure | 2 | - |
| Methyl alcohol (methanole) | | 1 | - |
| Methyl ethyl ketone | | 3 | 3 |
| Methylen chloride | | 3 | 3 |
| Milk | | 1 | 1 |
| Molasses | | 1 | - |
| Molasses wort | | 1 | 1 |

| | | | |
|---------------------------------|----------------------|---|---|
| Mowilith D | | 1 | 1 |
| Nitric acid | 100 % | 3 | 3 |
| Nitric acid | 1-10 % | 1 | 1 |
| Nitric acid | 50 % | 1 | 1 |
| Nitric acid | 66 % | 3 | 3 |
| Nitric acid | 70 % | 3 | 3 |
| Oil (vegetable) and animal fats | | 1 | - |
| Oleic acid | techn. pure | 1 | - |
| Oleum | 10 % SO ³ | 3 | 3 |
| Olive oil | | 1 | - |
| Oxalic acid | aqueous | 1 | 1 |
| Palm-oil | | 1 | - |
| Perchloric acid | | 3 | 3 |
| Petrol | | 1 | 1 |
| Petrol 10% ethyl alcohol | | 2 | - |
| Petrol 10% methanol | | 2 | - |
| Petrol normal | | 2 | - |
| Petrol normal unleaded | | 2 | - |
| Petrol Super unleaded | | 2 | - |
| Petroleum | | 1 | 1 |
| Phenol | 100 % | 3 | 3 |
| Phenol | 10 % | 3 | 3 |
| Phosphoric acid | 1-5 % | 1 | - |
| Photographic developers | | 1 | - |
| Phthalic acid | saturated | 1 | - |
| Plasticiser, DBS | | 1 | 1 |
| Plasticiser, DOP | | 1 | 1 |
| Potash | saturated | 1 | 1 |
| Potash | aqueous | 1 | 1 |
| Potassium bichromate | saturated | 2 | - |
| Potassium borate | 10 % | 1 | 1 |
| Potassium borate | aqueous | 1 | 1 |
| Potassium bromide | any | 1 | 1 |
| Potassium chloride | aqueous | 1 | - |
| Potassium hydroxide | 50 % | 3 | 3 |
| Potassium hydroxide | conc. | 3 | 3 |
| Potassium hydroxide | aqueous | 3 | 3 |
| Potassium hydroxide | 10 % | 3 | 3 |
| Potassium hydroxide | 1 % | 3 | 3 |
| Potassium nitrate | 50 % | 1 | 1 |
| Potassium nitrate | aqueous | 1 | 1 |
| Potassium permanganate | | 1 | 1 |
| Potassium permanganate | aqueous | 1 | 1 |
| Propane | liquid | 1 | - |
| Propane | gaseous | 1 | - |
| Propyl alcohol | | 1 | - |
| Propyl alcohol | 100 % | 1 | - |
| Sea water | | 1 | 1 |
| Silicic acid | any | 1 | 1 |
| Silicone oil | | 1 | - |
| Silver nitrate | | 1 | 1 |
| Silver nitrate | aqueous | 1 | 1 |
| Silver salt | saturated | 1 | 1 |
| Soap solution | any | 1 | 1 |
| Sodium carbonate | aqueous | 1 | - |
| Sodium carbonate | aqueous | 1 | - |
| Sodium chloride | any | 1 | 1 |

| | | | |
|------------------------------|-------------|---|---|
| Sodium chloride | aqueous | 1 | 1 |
| Sodium fluoride | saturated | 1 | 1 |
| Sodium hydroxide | 1 % | 2 | 2 |
| Sodium hydroxide | 50 % | 3 | 3 |
| Sodium hydroxide | 30 % | 3 | 3 |
| Sodium hydroxide | 45 % | 3 | 3 |
| Sodium hydroxide | 60 % | 3 | 3 |
| Sodium hydroxide | aqueous | 3 | 3 |
| Sodium hypochlorite | | 2 | 2 |
| Sodium hypochlorite | 12 % Cl | 2 | 2 |
| Sodium hypochlorite | 15 % | 2 | 2 |
| Sodium hypochlorite | 50 % | 3 | 3 |
| Sodium hypochlorite | saturated | 3 | 3 |
| Sodium hypochlorite | diluted | 2 | 2 |
| Sodium hypochlorite | aqueous | 2 | 2 |
| Sodium hypochlorite solution | 20 % | 3 | 3 |
| Sodium hypochlorite solution | 50 % | 3 | 3 |
| Sodium hypochlorite solution | diluted | 2 | - |
| Sodium nitrate | saturated | 1 | 1 |
| Sodium nitrate | aqueous | 1 | - |
| Sodium silicate | aqueous | 1 | - |
| Sodium silicate | any | 1 | - |
| Sodium sulfide | aqueous | 1 | - |
| Spindle oil | | 1 | - |
| Starch dilution | any | 1 | 1 |
| Starch sirup | | 1 | 1 |
| Stearic acid | crystals | 1 | - |
| Styrene | 100 % | 1 | 1 |
| Sugar sirup | | 1 | 1 |
| Sulphur | techn. pure | 1 | 1 |
| Sulphur trioxid | | 3 | 3 |
| Sulphuric acid | 40 % | 3 | 3 |
| Sulphuric acid | 60 % | 3 | 3 |
| Sulphuric acid | 80 % | 3 | 3 |
| Sulphuric acid | 95 % | 3 | 3 |
| Sulphuric acid | smoking | 3 | 3 |
| Tallow | techn. pure | 1 | - |
| Terpentine | | 1 | 1 |
| Terpentine oil | | 1 | - |
| Tetralin | | 1 | - |
| Toluene | | 1 | - |
| Transformer oil | 100 % | 1 | 1 |
| Trichlorethylene | 100 % | 3 | 3 |
| Triethanol amine | techn. pure | 1 | - |
| Urea | aqueous | 1 | - |
| Urea (carbamide) | | 1 | - |
| Urine | | 1 | - |
| Water | | 1 | 1 |
| Water, distilled/desalted | | 1 | 1 |
| Wax alcohol | techn. pure | 1 | - |
| Wine vinegar | | 1 | 1 |
| Wines | | 1 | 1 |
| Yeast | any | 1 | - |
| Zinc sulphate | 10 % | 1 | 1 |
| Zinc sulphate | aqueous | 1 | 1 |

AMORPHOUS PET CHEMICAL RESISTANCE

1 = Unaffected, 2 = Satisfactory, 3 = Some attack, 4 = Unsatisfactory

| Chemical | Concentration | Amorphous PET |
|----------------------|------------------|---------------|
| Acetic Acid | 40% aq | 1 |
| | Glacial | 3 |
| Acetic Anhydride | | 4 |
| Acetone | | 4 |
| Aluminium Sulphate | Solid | 1 |
| Ammonia | 10% aq | 4 |
| | 0.88 SG aq | 4 |
| Ammonium Chloride | solid | 1 |
| Ammonium Persulphate | solid | 1 |
| Ammonium Sulphate | solid | 1 |
| Amyl Acetate | | 3 |
| Amyl Alcohol | | 2 |
| Amyl Methyl Ketone | | 3 |
| Aniline | | 4 |
| Anthraquinone | solid | 1 |
| Barium Chloride | solid | 1 |
| Benzene | | 4 |
| Benzoic Acid | solid | 1 |
| Benzyl Acetate | | 4 |
| Benzyl Alcohol | | 4 |
| Benzyl Benzoate | | 3 |
| Butyl Acetate | | 4 |
| Butyl Alcohol | | 1 |
| Butyl Lactate | | 2 |
| Butyl Stearate | | 1 |
| Calcium Hypochlorite | solid | 2 |
| Camphor | solid | 1 |
| Camphorated Oil | | 2 |
| Carbon Tetrachloride | | 2 |
| Castor Oil | | 1 |
| Cetyl Alcohol | solid | 1 |
| Chloral Hydrate | solid | 4 |
| Chlorobenzene | | 4 |
| Chloroform | | 4 |
| Chromic Acid | plating solution | 4 |
| Citric Acid | | 1 |
| Citronellol | | 2 |
| Cupric Sulphate | solid | 1 |
| Cyclohexane | | 1 |
| Cyclohexanone | | 4 |
| Cyclohexanol | | 1 |
| Diacetone Alcohol | | 1 |
| Di-alkyl Phthalate | | 1 |
| Di-butyl Phthalate | | 1 |
| Di-nonyl Phthalate | | 2 |
| Di-octyl Phthalate | | 1 |
| Dimethyl Formamide | | 4 |
| Dioxane | | 4 |
| Dipentene | | 2 |
| Di-1-phenyl Ethanol | | 3 |
| 2-Ethoxy Ethanol | | 2 |

| | | |
|-----------------------|-------------|-----|
| Ethyl Acetate | | 4 |
| Ethyl Alcohol | | 1 |
| Ethyl Benzene | | 3 |
| Ethyl Digol | | 1 |
| Ethylene Chlorohydrin | | 4 |
| Ethylene Dibromate | | 4 |
| Ethyene Dichlorate | | 4 |
| Eugenol | | 4 |
| Ferric Nitrate | solid | 1 |
| Formaldehyde | 40% W/W aq | 1 |
| Formic Acid | 3% aq | 2 |
| | 30% aq | 2 |
| Furfuryl Alcohol | | 4 |
| Geraniol | | 2 |
| Glycerine | | 1 |
| Glycol | | 1 |
| Hydrobromic Acid | 50% aq | 1 |
| Hydrochloric Acid | 10% aq | 2 |
| Hydrofluoric Acid | 60% aq | 3 |
| | Conc | 4 |
| Hydrogen Peroxide | | 1 |
| Hydroquinone solid | | 1 |
| Isopropyl Alcohol | | 1 |
| Lanoline | | 1 |
| Linalol | | 2 |
| Linseed Oil | | 2 |
| Lubricating Grease | | 1 |
| Oil | | 1 |
| Magnesium Chloride | Aq solution | 2 |
| Maleic Acid | 25% | 2-4 |
| | 50% aq | 2 |
| Mercuric Chloride | solid | 1 |
| Mercury | | 1 |
| 2-Methoxy Ethanol | | 3 |
| Methyl Alcohol | | 1 |
| Methyl Cyclohexanol | | 1 |
| Methyl Ethyl Ketone | | 4 |
| Methyl Methacrylate | | 3 |
| Methyl Salicylate | | 4 |
| Methylene Chloride | | 4 |
| Mineral Oil | | 1 |
| Naphtha | Crude | 1 |
| | Solvent | 2 |
| Nitric Acid | 10% aq | 2 |
| n-Octane | | 1 |
| Olive Oil | | 2 |
| Oxalic Acid | Solid | 1 |
| | Solution | 2 |
| Paraffin | medicinal | 1 |
| Paraffin Oil | | 1 |
| Petrol | | 2 |
| Petroleum Ether | | 1 |
| Phenol | | 4 |
| Pinene | | 2 |
| Potassium Bromide | solid | 1 |
| Potassium Chromate | solid | 1 |
| Potassium Cyanide | solid | 1 |
| Potassium Dichromate | solid | 1 |

| | | |
|--------------------------|----------------------|----------|
| Potassium Hydroxide | 1% aq 10% aq | 4 4 |
| Potassium Permanganate | solid | 3 |
| Propionic Acid | | 4 |
| Propyl Alcohol | | 1 |
| Propylene Glycol | | 1 |
| Salicylic Acid | solid | 1 |
| Sodium Bicarbonate | solid | 1 |
| Sodium Borate | solid | 1 |
| Sodium Bromide | solid | 1 |
| Sodium Carbonate | Anhydrous 2.5% aq | 1 1 |
| Sodium Chloride | 1% aq 10% aq | 1 2 |
| Sodium Cyanide | solid | 1 |
| Sodium Hydroxide | 1% aq 10% aq | 4 4 |
| Sodium Nitrate | solid | 2 |
| Sodium Phosphate | solid | 1 |
| Sodium Sulphite | solid | 2 |
| Sodium Thiosulphate | solid | 1 |
| Stearic Acid | solid | 2 |
| Sulphur | solid | 1 |
| Sulphuric Acid | 3% aq 30% aq | 2-4 2 |
| Tartaric Acid | solid | 2 |
| Tetrahydrofuran | | 4 |
| Tetralin | | 1 |
| Toluene | | 2 |
| Transformer Oil | | 2 |
| Trichloroethyl Phosphate | | 1 |
| Trichloroacetic Acid | | 4 |
| Trichloroethylene | | 4 |
| Triethanolamine | | 4 |
| Vinegar | | 2 |
| Xylene | | 2 |
| Zinc Chloride | solid | 2 |

AMORPHOUS PET CHEMICAL RESISTANCE (b)

After immersion for 1 year @ 23°C

| Chemical | % change | | Appearance |
|---|----------|-----------|-------------------|
| | Weight | Thickness | |
| Acetic Acid, Concentrated | 9 | 7 | Milky |
| Acetic Acid, 5% | <1 | <5 | No change |
| Acetone | 11 | 12 | Grayish white |
| Ammonium Hydroxide, Concentrated | — | — | Degraded |
| Ammonium Hydroxide, 10% | — | — | Degraded |
| Benzyl Alcohol | 7 | 6 | Dull hazy |
| Brake Fluid, DOT 3 | <1 | <5 | Slightly yellow |
| Carbon Tetrachloride | <1 | <5 | No change |
| Citric Acid, 10% | <1 | <5 | No change |
| Cottonseed Oil | <1 | <5 | No change |
| Cyclohexanone | 14 | 16 | Gray |
| Detergent, 0.25% Alconox | <1 | <5 | No change |
| Dibutyl Sebacate | <1 | <5 | No change |
| Diesel Fuel | <1 | <5 | Light brown tint |
| Dimethylformamide | 20 | 20 | Milky |
| Distilled Water | <1 | <5 | No change |
| Di(2-ethylhexyl)phthalate | <1 | <5 | No change |
| Ethanol, 100% (Not Denatured) | <1 | <5 | No change |
| Ethanol, 50% (Not Denatured) | <1 | <5 | No change |
| Ethyl Acetate | 13 | 14 | Gray |
| Ethylene Glycol | <1 | <5 | No change |
| Freon TF | <1 | <5 | No change |
| Gasoline | <1 | <5 | No change |
| Grease, Automotive (Lithium) | <1 | <5 | No change |
| Heptane | <1 | <5 | No change |
| Hexane | <1 | <5 | No change |
| Hydrochloric Acid, Concentrated | — | — | Degraded |
| Hydrochloric Acid, 10% | <1 | <5 | No change |
| Hydrogen Peroxide, 28% | <1 | <5 | Yellow tint |
| Hydrogen Peroxide, 3% | <1 | <5 | No change |
| Isooctane | <1 | <5 | No change |
| Isopropanol | <1 | <5 | No change |
| Kerosene, K-1 | <1 | <5 | No change |
| Methanol | 1 | <5 | No change |
| Methyl Isobutyl Ketone | 1 | <5 | Hazy |
| Mineral Oil, White USP | <1 | <5 | No change |
| Motor Oil, 10-W-30 | <1 | <5 | No change |
| Nitric Acid, Concentrated | — | — | Degraded |
| Nitric Acid, 40% | 2 | <5 | Distorted, chalky |
| Nitric Acid, 10% | <1 | <5 | No change |
| Oleic Acid, 83% | <1 | <5 | No change |
| Olive Oil | 2 | <5 | Hazy |
| Perchloroethylene (Tetrachloroethylene) | 2 | <5 | Hazy |
| Phenol, 5% | 19 | 17 | White |
| Soap Solution, 1% | <1 | <5 | No change |
| Sodium Chloride, 10% | <1 | <5 | No change |
| Sodium Hydroxide, 30% | — | — | Degraded |
| Sodium Hydroxide, 10% | 221 | 217 | Hazy |
| Sodium Hydroxide, 1% | 21 | <5 | Hazy |
| Sodium Hypochlorite, 3.5% | <1 | <5 | Slightly chalky |
| Sulfuric Acid, Concentrated | — | — | Degraded |

| | | | |
|--------------------------------|-----|-----|-----------|
| Sulfuric Acid, 30% | <1 | <5 | No change |
| Sulfuric Acid, 3% | <1 | <5 | No change |
| Tetrahydrofuran | >20 | >20 | Chalky |
| Toluene | 6 | 6 | Hazy |
| Transformer Oil | <1 | <5 | Hazy |
| Transmission Fluid, Automotive | <1 | <5 | No change |
| 1,1,1-Trichloroethane | 2 | <5 | Hazy |
| Turpentine | <1 | <5 | No change |